



# RAJ CERAMICS

## Z ACID MORTAR

Sl. No.	Brand	Working Time Minutes at 27°C	Flexural Strength (Kg/cm <sup>2</sup> ) min	C.C.S. (Kg/cm <sup>2</sup> ) min	Bond Strength (Kg/cm <sup>2</sup> ) min	Absorption of toluene max. (% by weight)	Remarks
1	RC-AM (SS)	15	35	100	5	18	Outsourced
2	RC-AM (PS)	29	40	150	5	18	Outsourced



1. The above values represent values obtained on standard squares in accordance with accepted test methods and are subject to manufacturing variations. This information is supplied as a technical service and may change without notice. Results are only indicative data and should not be used for specification/guarantee purposes. Size tolerance  $\pm 1.5\%$  or  $\pm 2\text{mm}$  whichever ever is greater.
2. We also make Bricks on tailor-made specification
3. Grading means 90% passing through the desired sieve

