



# RAJ CERAMICS

## T CEMENT

Sl. No.	Brand	Al <sub>2</sub> O <sub>3</sub> % min	SiO <sub>2</sub> % max	CaO % max	Fe <sub>2</sub> O <sub>3</sub> % max	MgO %max	PCE OC min	Specific Surface	Specific Gravity	Final	C.C.S (Kg/cm <sup>2</sup> )	
											After 6 hr.	After 1 day
1	RC - Calal 75	72	0.7	24	0.3	0.8	31	4000	2.90-2.95	400	125	350
2	RC - Calal 50	48	4	35	5	0.9	13-14	3000	-	400	150	450

For quick setting cement, specify seperating in your enquiry.



- 1. The above values represent values obtained on standard squares in accordance with accepted test methods and are subject to manufacturing variations. This information is supplied as a technical service and may change without notice. Results are only indicative data and should not be used for specification/guarantee purposes. Size tolerance  $\pm 1.5\%$  or  $\pm 2\text{mm}$  which ever is greater.
- 2. We also make Bricks on tailor-made specification
- 3. Grading means 90% passing through the desired sieve

