



# RAJ CERAMICS

## Y NOZZLE

Sl. No.	Brand	Al <sub>2</sub> O <sub>3</sub> % min	Fe <sub>2</sub> O <sub>3</sub> % max	PCE OC min	A.P. (%) max	B.D. (GM/cc)	CCS in Block	MgO % min
1	RC - HAN	60	1.5	35	22	2.45	250	-
2	RC - HAN (S)	70	2	36	20	2.55	-	-
3	RC - MGTN	-	1	36	20	2.85	250	70



1. The above values represent values obtained on standard squares in accordance with accepted test methods and are subject to manufacturing variations. This information is supplied as a technical service and may change without notice. Results are only indicative data and should not be used for specification/guarantee purposes. Size tolerance  $\pm 1.5\%$  or  $\pm 2\text{mm}$  whichever is greater.
2. We also make Bricks on tailor-made specification
3. Grading means 90% passing through the desired sieve

