



RAJ CERAMICS

J RAMMING MASS

Sl. No.	Brand	Al ₂ O ₃ % min	Fe ₂ O ₃ % max	PCE OC min	Grading Range	Setting type	Service Temp °C
1	RC - Ram - 40	40	2.0	33	0-4 mm	Ceramic	1450
2	RC - Ram - 60	60	2.5	34	0-4 mm	Chemical	1600
3	RC - Ram - 70	70	3.0	35	0-4 mm	Chemical/Ceramic	1650
4	RC - Ram - 80	80	3.5	36	0-4 mm	Chemical	1700
5	RC - Ram - 90 (S)	90	1.5	37	0-4 mm	Chemical	1750



1. The above values represent values obtained on standard squares in accordance with accepted test methods and are subject to manufacturing variations. This information is supplied as a technical service and may change without notice. Results are only indicative data and should not be used for specification/guarantee purposes. Size tolerance $\pm 1.5\%$ or $\pm 2\text{mm}$ whichever is greater.
2. We also make Bricks on tailor-made specification
3. Grading means 90% passing through the desired sieve

