



RAJ CERAMICS

K RAMMING MASS FOR INDUCTION

Sl. No.	Brand	SiO ₂ % min	MgO % min	PCE OC min	Grading Range	Setting type	Service Temp °C
1	RC - Quartz	97	-	31	0-5	Chemical	1680
2	RC - Quartzite	98	-	32	0-5	Chemical	1700
3	RC - Magnesite	-	85	35	0-5	Chemical	1750
4	RC - MC	1.0	96	36	0-5	Chemical	1750

For IF – Ladle (Silica Ramming Mass) application, tailormade solution provided



1. The above values represent values obtained on standard squares in accordance with accepted test methods and are subject to manufacturing variations. This information is supplied as a technical service and may change without notice. Results are only indicative data and should not be used for specification/guarantee purposes. Size tolerance $\pm 1.5\%$ or $\pm 2\text{mm}$ whichever is greater.
2. We also make Bricks on tailor-made specification
3. Grading means 90% passing through the desired sieve

