



# RAJ CERAMICS

## L RAMMING MASS SPECIAL

Sl. No.	Brand	Al <sub>2</sub> O <sub>3</sub> % min	ZrO <sub>2</sub> % max	Grading Range	Setting type	Sintering Temp °C
1	RC - Ram ZS	-	50	0-3 mm	Chemical	1150
2	RC - Ram ZM	55	24	0-3 mm	Chemical	1100
3	RC - Patch ZS	-	50	0-2 mm	Chemical	1100



1. The above values represent values obtained on standard squares in accordance with accepted test methods and are subject to manufacturing variations. This information is supplied as a technical service and may change without notice. Results are only indicative data and should not be used for specification/guarantee purposes. Size tolerance  $\pm 1.5\%$  or  $\pm 2\text{mm}$  whichever ever is greater.
2. We also make Bricks on tailor-made specification
3. Grading means 90% passing through the desired sieve

